

## Study on adsorption performance of different adsorbents in CO<sub>2</sub>/N<sub>2</sub> separation

Behnam Rezazadeh<sup>1</sup>: Amin alamdari<sup>\*2</sup>

1. PhD. Student of Chemical Engineering, Faculty of chemical Engineering, sahand University of Technology, Tabriz, Iran
- \*2. Assistant Professor, Faculty of Engineering, Department of Chemical Engineering, Urmia University, Urmia, Iran

\*Email Address::[a.alamdari@urmia.ac.ir](mailto:a.alamdari@urmia.ac.ir)

### Article Info

#### Article Type:

Research Paper

#### Article History:

Received Date:

**2025/06/04**

Revised Date:

**2025/07/18**

Accepted Date:

**2025/08/27**

Published Date:

**2025/09/30**

#### Keywords:

Adsorption,

Nitrogen,

Carbon oxide,

Ideal Adsorption Solution Theory (IAST).

### ABSTRACT

There are diverse adsorbents have different capacities with various ideal selectivities for CO<sub>2</sub>/N<sub>2</sub> separation. Among the different adsorbents, a comprehensive comparison should be made to find the more appropriate adsorbent for a desired process. In this paper, equilibrium adsorbed amount and selectivity of adsorbents are investigated using the Ideal Adsorption Solution Theory (IAST) to determine suitable adsorbents for CO<sub>2</sub>/N<sub>2</sub> separation. Model (IAST) was used to compare the adsorbents in different pressures (1 - 100 kpa) and in gas compositions (50 – 50) also, at pressure 100 kpa was used. The results revealed that Activated - Zeolite adsorbent at 298K have higher equilibrium adsorption selectivities. Among them, KIT - 6 has the highest capacity. The results showed that the adsorbent Zeolite 13X has lower selectivity and lower adsorption capacity than other adsorbents. Finally, a novel trade-off plot of adsorbed amount versus selectivity was constructed as guide for researcher's applications.

### Cite this article:

Behnam Rezazadeh: Amin alamdari (2025). Study on adsorption performance of different adsorbents in carbon dioxide /nitrogen separation , journal of Environmental Sciences Studies, 10(3), Pages 10575-10582 .

## EXTENDED ABSTRACT

### Introduction

CO<sub>2</sub> emission from fossil fuel combustion is considered as one of the main issues of environmental problems and global warming have actuated the re searches on CO<sub>2</sub> separation from flue gas. However, various methods have been used to removing CO<sub>2</sub> from natural gas and flue gas, among which the adsorption is considered as a more cost - effective technical solution, along with low energy consumption, simple design, environmental efficient method. On the other hand, there is no simple comparison between the performance of the absorbents. in this regard, a method it can be used to select an appropriate adsorbent with high selectivity and selectivity, coupled with the effect of operating conditions on performance, the ideal adsorption solution theory (IAST). Theory IAST is one of the most reliable methods for predicting adsorption equilibrium of gas mixtures, which is often used to predict the equilibrium of mixture of gas mixture and only uses pure component absorption. for CO<sub>2</sub>/N<sub>2</sub> separation, various adsorbents were reported .in this research, CO<sub>2</sub>/N<sub>2</sub> adsorbents were compared with the calculations of two - component mixture adsorption by use IAST under pressure of 1 - 100 kpa .at the end, a new commercial design of the adsorption values as a simple guide for researchers for industrial applications for the selection of high - performance adsorbents for the separation of CO<sub>2</sub>/N<sub>2</sub> has been prepared.

### Theory and modeling: IAST method

one of the most popular methods is this method is one of the most widely used models to predict the balance in multicomponent mixtures. the advantages of this method are high speed, simple calculations, thermodynamic stability, and the ability to use all existing equilibrium isotherms. This theory assumes that the adsorbed mixture is an ideal solution, where there is no interaction between the components present in the adsorption phase. This theory is based on thermodynamic solutions which is independent of the real adsorption model. Different versions of this theory have been proposed that are continued by prausnitz that are extended for fast systems and other versions such as vermeilen have been developed and developed by Luan which can be used to improve the speed of calculations in this research, by using ideal adsorption solution and related MATLAB program, two - component mixture adsorption modeling was investigated. Variations in selectivity versus pressure changes as well as the difference between the absorbents in the selectivity and the total uptake for different adsorbents were introduced. for the two - component adsorption calculations, the adsorption data of pure component is required.

### Results and discussion

by changing the operating pressure in the range of 1 - 100 kPa for the gas mixture (50 - 50) CO<sub>2</sub>/N<sub>2</sub>, different adsorbents were investigated. The results show that by increasing the pressure on the adsorbent type, the amount of carbon dioxide adsorbed increases with further increase or is not significantly changed. Also, it is shown that the effect of increasing pressure leads to an increase in absorption rate. Also, for the activated carbon - AQSOA FAM Z02 - KIT-6 a adsorbent, a very little change in the absorption rate is created. Also, by increasing the selectivity of MIL 100 (Fe) - Activated carbon/zeolit, as expected, we see more selectivity at low temperatures the selectivity of adsorbent is more than other adsorbents. In this absorber, the selectivity is increased by increasing the selectivity, the adsorbent has a selectivity at 303 k and the adsorbent KIT-6 the most has the total uptake. On the other hand, MOF-505@GO adsorbent has less selectivity and less adsorption capacity than other adsorbents. however, the choice of the absorber should be based on economic calculations.

### Conclusion

the performance of different adsorbents was investigated for CO<sub>2</sub>/N<sub>2</sub> separation using the idea of al adsorption solution. all of the studied adsorbents include zeolite, MOF and activated carbons to CO<sub>2</sub>. Among all the adsorbents MIL-100(Fe) and Activated carbon/zeolite and activated/zeolite adsorbents have selectivity to CO<sub>2</sub>/N<sub>2</sub>, respectively. among the selected adsorbents, the highest CO<sub>2</sub>absorption belongs to KIT-6 the obtained diagram of co2 absorption in the presence of CO<sub>2</sub> selectivity for different adsorbents is prepared which is a suitable guide for selecting appropriate adsorbent for industrial applications of these adsorbents.



## مقایسه جذب سطحی تعادلی جاذب‌های مختلف در جداسازی CO<sub>2</sub> /N<sub>2</sub>

بهنام رضازاده<sup>۱</sup>، امین علمداری<sup>۲\*</sup>

۱- دانشجوی دکتری مهندسی شیمی، دانشکده مهندسی شیمی، دانشگاه صنعتی سهند

۲\* -استادیار مهندسی شیمی، دانشکده فنی، دانشگاه ارومیه

\* ایمیل نویسنده مسئول: a.alamdari@urmia.ac.ir

چکیده	اطلاعات مقاله
جاذب‌های مختلفی برای جداسازی گازهای نیتروژن و دی اکسید کربن با ظرفیت جذب و انتخاب‌گری متفاوت وجود دارند. در بین جاذب‌های مختلف، باید مقایسه جامعی جهت انتخاب جاذب مناسب برای یک فرایند مطلوب صورت گیرد. در این مقاله، مقدار جذب تعادلی و انتخاب‌پذیری جاذب‌های مختلف با استفاده از تئوری محلول جذب ایده‌آل (IAST) برای تعیین جاذب مناسب برای جداسازی گازهای نیتروژن و دی اکسید کربن بررسی شده است. مدل IAST برای مقایسه جاذب‌ها در فشارهای مختلف (۱ تا ۱۰۰ کیلو پاسکال) و در ترکیب درصد ۵۰-۵۰ مخلوط گاز CO <sub>2</sub> /N <sub>2</sub> جهت مقایسه جاذب‌های مختلف در فشار کل ۱۰۰ کیلو پاسکال استفاده شده است. نتایج نشان داد، جاذب کربن فعال/زئولیت در دمای ۲۹۸ کلوین بیشترین میزان انتخاب‌پذیری و جاذب KIT-6 بیشترین میزان جذب کل را دارد. بررسی‌ها نشان داد، جاذب Zeolite 13X انتخاب‌پذیری و ظرفیت جذب کمتری نسبت به دیگر جاذب‌ها دارد. در انتها نمودار جدید trade - off، بر اساس میزان جذب در برابر انتخاب‌پذیری جاذب‌های مختلف جهت راهنمایی محقق برای استفاده در کاربردهای صنعتی تهیه شد.	<b>نوع مقاله:</b> مقاله علمی پژوهشی  <b>تاریخ دریافت:</b> ۱۴۰۴/۰۳/۱۴ <b>تاریخ بازنگری:</b> ۱۴۰۴/۰۴/۲۷ <b>تاریخ پذیرش:</b> ۱۴۰۴/۰۶/۰۵ <b>تاریخ انتشار:</b> ۱۴۰۴/۰۷/۰۸  <b>کلید واژه‌ها:</b> جذب سطحی، نیتروژن، دی اکسید کربن، تئوری محلول جذب ایده‌آل (IAST)

## ۱- مقدمه

شرایط زیست محیطی کره زمین با انتشار بیش از اندازه گاز دی اکسیدکربن و دیگر گازهای گلخانه‌ای در حال تغییر می‌باشد. به طوری که با افزایش قابل توجه تولید گازهای گلخانه‌ای و ورود به محیط زیست، باعث ایجاد مشکلات زیست محیطی همچون افزایش دما، آسیب دیدن لایه اوزون و دیگر عوامل مخرب زیست محیطی می‌شود (Gomes et al, 2002). جهت کاهش اثرات مخرب محیط زیستی گازهای گلخانه‌ای، باید از وارد شدن گازهای گلخانه‌ای که یکی از مهم‌ترین این گازها دی اکسیدکربن ( $CO_2$ ) می‌باشد، به اتمسفر جلوگیری کرد (Pellerano et al, 2009). فرآیندهای مختلفی برای حذف دی اکسیدکربن وجود دارد که شامل جذب با محلول آمین، جداسازی غشایی و جذب سطحی با انواع مختلف جاذب‌ها می‌باشند (Chang et al. ; 2004 To et al, 2016). در میان روش‌های مختلف برای جداسازی دی اکسید کربن  $CO_2$ ، جذب سطحی دارای مزایای سرمایه گذاری اولیه اندک، راندمان جذب بالا، عملکرد ساده، روش‌های احیا آسان برای جاذب‌ها، مصرف کم انرژی و سازگاری بیشتر با محیط زیست است (Hansen et al.; 2016). Li et al, 1988 جاذب‌هایی که تاکنون برای جذب  $CO_2$  مورد بررسی قرار گرفته، مشخص شده است که عملکرد موثر جذب این گاز به ترکیبی از نفوذ و گزینش پذیری جذب بستگی دارد بنابراین، یک جاذب مناسب شامل میکرو حفرات زیاد با اندازه منافذ مناسب میکرو حفره با قطر کمتر از (۷۰ نانومتر) برای جذب بالای  $CO_2$  و همچنین وجود منافذ بزرگتر، برای افزایش نفوذ  $CO_2$  مناسب است (Sakuth et al. ; 1998 Cessford et al, 2012). از طرفی مقایسه ساده‌ای بین عملکرد این جاذب‌ها وجود ندارد. در این راستا، روشی که می‌تواند برای انتخاب جاذب مناسب با میزان انتخاب‌پذیری و جذب بالا همراه با تأثیر شرایط عملیاتی بر عملکرد مورد استفاده قرار گیرد، تئوری محلول جذب ایده‌ال (IAST) می‌باشد (Myers et al.; 1965 Huwae et al, 2024). IAST یکی از مطمئن‌ترین روش‌ها برای پیش بینی تعادل جذب مخلوط گازها می‌باشد که اغلب برای پیش بینی تعادل جذب مخلوط گاز استفاده می‌شود و فقط از همدماهای جذب جزء خالص استفاده می‌کند. برای جداسازی  $CO_2/N_2$ ، جاذب‌های مختلفی گزارش شده است که در جدول (۱) نشان داده شده است. در این پژوهش، جاذب‌های  $CO_2/N_2$  با محاسبات جذب مخلوط دو جزئی با استفاده از تئوری IAST در شرایط فشارهای ۱ تا ۱۰۰ کیلو پاسکال مقایسه شده‌اند. در انتها، یک طرح تجاری جدید از مقادیر جذب شده در برابر انتخاب‌پذیری به عنوان یک راهنمای ساده برای محققان جهت کاربردهای صنعتی برای انتخاب جاذب‌های با کارایی بالا برای جداسازی  $CO_2/N_2$  تهیه شده است.

## ۲- تئوری و مدل سازی روش IAST

با توجه به اینکه اندازه‌گیری داده‌های تعادل مخلوط چند جزئی در دما، فشار و ترکیبات مختلف یک فرایند دشوار است، مدل‌های مختلفی برای تخمین جذب تعادلی مخلوط چند جزئی با استفاده از داده‌های همدما ارائه شده است. یکی از معروف‌ترین روش‌ها IAST می‌باشد (Keshavarz et al, 2021) که این روش یکی از پرکاربردترین مدل‌ها برای پیش بینی تعادل در مخلوط چند جزئی است. از مزایای این روش می‌توان به سرعت بالا، محاسبات ساده، پایداری ترمودینامیکی و توانایی استفاده از همه همدماهای تعادل موجود اشاره کرد. این تئوری، فرض می‌کند که مخلوط جذب شده یک راه حل ایده‌آل است که در آن هیچ تعاملی بین اجزای موجود در مرحله جذب وجود ندارد (Zagho et al, 2021). تئوری IAST براساس محلول‌های ترمودینامیکی می‌باشد که مستقل از مدل واقعی جذب سطحی است. نسخه‌های مختلفی از این تئوری ارائه شده است که توسط مایرز و پرازنیتز<sup>۱</sup> که برای (Fast IASTv) برای سیستم‌های دو جزئی ادامه یافته و نسخه‌های دیگری مثل ورمویلن<sup>۲</sup> شروع و توسط لوان<sup>۳</sup> توسعه یافته که برای بهبود سرعت محاسبات می‌باشد (Aghel et al, 2022 Boonchuay et al, 2022). در این پژوهش، با استفاده از تئوری IAST و برنامه نویسی متلب مربوطه به مدل‌سازی جذب مخلوط دو جزئی پرداخته شده است. تغییرات انتخاب‌پذیری در مقابل تغییرات فشار و نیز مقایسه‌ای بین جاذب‌ها در انتخاب‌پذیری و میزان جذب کل برای جاذب‌های مختلف معرفی شده است. برای محاسبات مخلوط دو جزئی جذب سطحی، نیاز به داده‌های همدمای جذب سطحی جزء خالص می‌باشد. داده‌های یاد شده از مقالات مربوطه استخراج و در جدول (۱) برای نیتروژن و کربن دی‌اکسید گزارش شده است. همدماهای تعادلی مورد استفاده، همدمای لانگمویر معادله (۱)، همدمای تاد معادله (۲) و همدمای سیپس معادله (۳) است. لازم به ذکر است مقدار جذب در واحد جرم جاذب (q)، ضریب میل (b)، پارامتر ناهمگنی (n - t) و فشار تعادلی (p) می‌باشد.

<sup>1</sup> Myers and Prausnitz

<sup>2</sup> Vermeilen

<sup>3</sup> Luan

$$q = q^{sat} \frac{pb}{1+pb} \quad (1)$$

$$q = q \frac{bp}{(1+(bp)^t)^t} \quad (2)$$

$$q = q^{sat} \frac{bp^{\frac{1}{n}}}{1+bp^{\frac{1}{n}}} \quad (3)$$


جدول ۱. پارامترهای همدمای جذب نیتروژن و دی اکسید کربن برای جاذب‌های مختلف

Reference	n, t	Isotherm	b (kpa <sup>-1</sup> )		q <sup>sat</sup> (mmol/g)		T(K)	Adsorbent
			CO <sub>2</sub>	N <sub>2</sub>	CO <sub>2</sub>	N <sub>2</sub>		
Rostami et al	۰,۴۷	Toth	۰,۰۰۱۸	۰,۰۰۰۴	۱,۳۲	۰,۴۴	۳۰۳	Activated Carbon-Zeolite
Qasem et al	۱	Langmuir	۰,۰۱۳	۰,۰۱	۳,۲۴	۳,۲۱	۳۲۴	Zeolite 13X
Wu et al	1	Langmuir	۰,۰۰۱۸	۰۰۴۵,۰	۳	۲,۱	۲۹۸	HCP
Zhang et al	۰,۸	Toth	۰,۰۰۲۲	0.0025	۱,۳	۱,۲	313	Activated carbon
Charalambous et al	۰,۶۲	Toth	۰,۰۱۰۶	0.۰۰۰۱۴	۶,۰۶	۶,۰۶	۲۹۸	AQSOA FAM Z02
Ning et al	۱	Langmuir	۰,۰۰۰۳	۰,۰۰۵۱	۵,۲۵	۲,۲	۲۹۸	K-SCNG
Mendes et al	۰,۶۲	Toth	۰,۰۰۱۲	۰,۰۰۳۳	۵,۱۱	۵,۴۲	305	5A zeolite
Xian et al	۱	Langmuir	۰,۰۰۵۲	۰,۰۰۰۴	۳,۲	۲	۳۰۳	PEI@ZIF-8
Chen et al	۱	Langmuir	۰,۰۰۰۵۱	۰,۰۰۲۶	۵,۳	۳,۲	298	MOF-505@GO
Goyal et al	۱	Langmuir	۰,۰۰۴۱	0.۰۰۲۰۵	۶,۱	۳۲,۲	۳۰۵	Silica Gel
Xian et al	۱	Langmuir	۰,۰۰۰۶	0.۰۰۲۱	۷	۳	۲۹۸	MIL-100 (Fe)
Xu et al	۱	Langmuir	۰,۰۰۱۲	0.۰۰۷۲	۶,۵۵	۴,۱۶	298	Hyper crosslinked polymer (HCP)
Moradi et al	۰,۵۶	Sips	۰,۰۰۵۶	0.۰۰۶۳	۱۶,۴	۰,۰۰۱۵	۳۰۵	GrO@HKUST
Ramezani pour et al	۱	Langmuir	۰,۰۰۲۹	0.۰۱۰۲۰	۶,۲	۳,۱۸	۳۰۵	HNPC
Rupak et al	۰,۷۵	Sips	۰,۰۰۷۶	۰,۰۰۱۵	۵,۱	۲,۸	۲۹۸	KIT-6

### ۳- نتایج

#### • تاثیر فشار بر میزان جذب


با توجه به شکل (۱)، با تغییر فشار عملیاتی در محدوده ۱-۱۰۰ کیلوپاسکال برای مخلوط گازی (۵۰-۵۰) CO<sub>2</sub>/N<sub>2</sub>، میزان جذب جاذب‌های مختلف بررسی شد. نتایج نشان می‌دهد، با افزایش فشار بسته به نوع جاذب میزان جذب دی اکسید کربن افزایش با شدت بیشتر افزایش می‌یابد و یا به طور قابل توجه تغییر نمی‌کند. به‌طوریکه در جاذب‌های AQSOA FAM Z02 - activated carbon - 5A - GrO@HKUST افزایش فشار منجر به افزایش قابل توجه میزان جذب می‌شود. همچنین برای جاذب‌های zeolite تغییر بسیار کمی در میزان جذب ایجاد می‌شود.




شکل ۱. میزان جذب دی اکسید کربن در فشارهای مختلف  $CO_2/N_2$  در ترکیب درصد ۵۰-۵۰.

#### • انتخاب پذیری جاذبها در فشارهای مختلف

با توجه به شکل (۲) جاذب MOF 505@GO - PE@ZIF-8 - HNPC در دمای ۲۹۸ کلون با افزایش فشار، انتخاب پذیری آن کاهش می یابد ولی جاذبهای دیگر نیز با افزایش فشار، انتخاب پذیری آنها تقریباً ثابت می ماند. همچنین با افزایش فشار انتخاب پذیری جاذب Activated carbon/zeolite - MIL 100 (Fe) افزایش می یابد به طوری که، در دماهای پایین انتخاب پذیری بیشتری را شاهد هستیم. در شکل (۲) انتخاب پذیری جاذب Activated carbon/zeolite بیشتر از جاذبهای دیگر می باشد و نیز در این جاذب با افزایش فشار انتخاب پذیری آن افزایش می یابد. با توجه به شکل (۲) جاذب Activated carbon/zeolite در دمای 303 کلون بیشترین میزان انتخاب پذیری را دارد و جاذب KIT-6 بیشترین میزان کل جذب را دارا می باشد. از طرفی، جاذب MOF-505@GO انتخاب پذیری و ظرفیت جذب کمتری در مقایسه با دیگر جاذبها دارد. با این وجود، انتخاب جاذب باید بر اساس محاسبات اقتصادی باشد. با توجه به نمودار شکل (۳) نتایج نشان می دهد، جاذب Activated carbon/zeolite می تواند در جذب و جداسازی  $CO_2$  از  $N_2$  عملکرد مطلوبی دارد. به طوری که جاذب KIT-6 می تواند به دلیل داشتن ظرفیت جذب بالا برای خالص سازی و حذف دی اکسید کربن از نیتروژن، و انتخاب پذیری بیشتر مورد استفاده قرار گیرد.



شکل ۲. (A) انتخاب پذیری تعادلی در فشارهای مختلف برای انتخاب پذیری پایین. (B) انتخاب پذیری تعادلی در فشارهای مختلف برای انتخاب پذیری بالای  $CO_2/N_2$  در ترکیب درصد ۵۰-۵۰.



شکل ۳. انتخاب پذیری دی اکسید کربن / نیتروژن در برابر میزان جذب جاذب‌های مختلف در دمای ۲۹۸ کلوین.

#### ۴- نتیجه‌گیری

عملکرد جاذب‌های مختلف جهت جداسازی  $\text{CO}_2/\text{N}_2$  با استفاده از نظریه محلول جذب ایده آل مورد بررسی قرار گرفت. تمامی جاذب‌های مورد مطالعه شامل زئولیت‌ها، MOF ها، و کربن‌های فعال نسبت به  $\text{CO}_2$  انتخاب پذیر هستند. در بین تمامی جاذب‌ها MIL-100(Fe) و Activated carbon/zeolite به ترتیب بیشترین انتخاب‌پذیری را نسبت به  $\text{CO}_2/\text{N}_2$  دارند. در میان جاذب‌های انتخابی، بیشترین میزان جذب  $\text{CO}_2$  متعلق به KIT-6 است. نمودار به دست آمده از مقادیر جذب شده  $\text{CO}_2$  در مقابل انتخاب پذیری  $\text{CO}_2$  برای جاذب‌های مختلف تهیه شده است که راهنمای مناسبی جهت انتخاب جاذب مناسب برای کاربردهای صنعتی این انواع جاذب‌ها می‌باشد.

#### منابع

- Aghel, B., Behaein, S., & Alobaid, F. (2022). CO<sub>2</sub> capture from biogas by biomass-based adsorbents: A review. *Fuel*, 328, 125276.
- Boonchuay, A., & Worathanakul, P. (2022). The diffusion behavior of CO<sub>2</sub> adsorption from a CO<sub>2</sub>/N<sub>2</sub> gas mixture on zeolite 5A in a fixed-bed column. *Atmosphere*, 13(4), 513.
- Cessford, N. F., Seaton, N. A., & Düren, T. (2012). Evaluation of ideal adsorbed solution theory as a tool for the design of metal-organic framework materials. *Industrial & engineering chemistry research*, 51(13), 4911-4921.
- Chang, D., Min, J., Moon, K., Park, Y. K., Jeon, J. K., & Ihm, S. K. (2004). Robust numerical simulation of pressure swing adsorption process with strong adsorbate CO<sub>2</sub>. *Chemical engineering science*, 59(13), 2715-2725.
- Charalambous, C., Santori, G., Vilarrasa-Garcia, E., Bastos-Neto, M., Cavalcante Jr, C. L., & Brandani, S. (2018). Pure and binary adsorption of carbon dioxide and nitrogen on AQSOA FAM Z02. *Journal of Chemical & Engineering Data*, 63(3), 661-670.
- Chen, Y., Lv, D., Wu, J., Xiao, J., Xi, H., Xia, Q., & Li, Z. (2017). A new MOF-505@ GO composite with high selectivity for CO<sub>2</sub>/CH<sub>4</sub> and CO<sub>2</sub>/N<sub>2</sub> separation. *Chemical Engineering Journal*, 308, 1065-1072.
- Gomes, V. G., & Yee, K. W. (2002). Pressure swing adsorption for carbon dioxide sequestration from exhaust gases. *Separation and purification technology*, 28(2), 161-171.
- Goyal, P., Purdue, M. J., & Farooq, S. (2019). Adsorption and diffusion of N<sub>2</sub> and CO<sub>2</sub> and their mixture on silica gel. *Industrial & Engineering Chemistry Research*, 58(42), 19611-19622.
- Hansen, J., Fung, I., Lacis, A., Rind, D., Lebedeff, S., Ruedy, R., & Stone, P. (1988). Global climate changes as forecast by Goddard Institute for Space Studies three-dimensional model. *Journal of geophysical research: Atmospheres*, 93(D8), 9341-9364.

- Huwae, R., Nuriyadi, M., & Tjiptadi, A. T. (2024). Equilibrium Volumetric Experiment Apparatus Review for Mixed-Gas Adsorption. In *Journal of Physics: Conference Series* (Vol. 2739, No. 1, p. 012009). IOP Publishing.
- Keshavarz, L., Ghaani, M. R., MacElroy, J. D., & English, N. J. (2021). A comprehensive review on the application of aerogels in CO<sub>2</sub>-adsorption: Materials and characterisation. *Chemical Engineering Journal*, 412, 128604.
- Li, J., Jia, D., Guo, Z., Liu, Y., Lyu, Y., Zhou, Y., & Wang, J. (2017). Imidazolium based porous hypercrosslinked ionic polymers for efficient CO<sub>2</sub> capture and fixation with epoxides. *Green Chemistry*, 19(11), 2675-2686.
- Mendes, P. A., Ribeiro, A. M., Gleichmann, K., Ferreira, A. F., & Rodrigues, A. E. (2017). Separation of CO<sub>2</sub>/N<sub>2</sub> on binderless 5A zeolite. *Journal of CO<sub>2</sub> utilization*, 20, 224-233.
- Moradi, M. R., Torkashvand, A., Ramezanipour Penchah, H., & Ghaemi, A. (2023). Amine functionalized benzene based hypercrosslinked polymer as an adsorbent for CO<sub>2</sub>/N<sub>2</sub> adsorption. *Scientific Reports*, 13(1), 9214.
- Myers, A. L., & Prausnitz, J. M. (1965). Thermodynamics of mixed-gas adsorption. *AIChE journal*, 11(1), 121-127.
- Ning, H., Yang, Z., Wang, D., Meng, Z., Li, Y., Ju, X., & Wang, C. (2021). Graphene-based semi-coke porous carbon with N-rich hierarchical sandwich-like structure for efficient separation of CO<sub>2</sub>/N<sub>2</sub>. *Microporous and Mesoporous Materials*, 311, 110700.
- Pellerano, M., Pré, P., Kacem, M., & Delebarre, A. (2009). CO<sub>2</sub> capture by adsorption on activated carbons using pressure modulation. *Energy procedia*, 1(1), 647-653.
- Qasem, N. A., & Ben-Mansour, R. (2018). Adsorption breakthrough and cycling stability of carbon dioxide separation from CO<sub>2</sub>/N<sub>2</sub>/H<sub>2</sub>O mixture under ambient conditions using 13X and Mg-MOF-74. *Applied energy*, 230, 1093-1107.
- Ramezanipour Penchah, H., Ghanadzadeh Gilani, H., & Ghaemi, A. (2020). CO<sub>2</sub>, N<sub>2</sub>, and H<sub>2</sub> adsorption by hyper-cross-linked polymers and their selectivity evaluation by gas–solid equilibrium. *Journal of Chemical & Engineering Data*, 65(10), 4905-4913.
- Rostami, M., Mofarahi, M., Karimzadeh, R., & Abedi, D. (2016). Preparation and characterization of activated carbon–zeolite composite for gas adsorption separation of CO<sub>2</sub>/N<sub>2</sub> system. *Journal of Chemical & Engineering Data*, 61(7), 2638-2646.
- Rupak, K., & Kumar, G. A. (2016). Polyethylenimine Functionalized As-Synthesized KIT-6 Adsorbent for Highly CO<sub>2</sub>/N<sub>2</sub> Selective Separation.
- Sakuth, M., Meyer, J., & Gmehling, J. (1998). Measurement and prediction of binary adsorption equilibria of vapors on dealuminated Y-zeolites (DAY). *Chemical Engineering and Processing: Process Intensification*, 37(4), 267-277.
- To, J. W., He, J., Mei, J., Haghpanah, R., Chen, Z., Kurosawa, T. & Bao, Z. (2016). Hierarchical N-doped carbon as CO<sub>2</sub> adsorbent with high CO<sub>2</sub> selectivity from rationally designed polypyrrole precursor. *Journal of the American Chemical Society*, 138(3), 1001-1009.
- Wu, Y., Wang, J., Muhammad, Y., Subhan, S., Zhang, Y., Ling, Y. & Zhao, Z. (2018). Pyrrolic N-enriched carbon fabricated from dopamine-melamine via fast mechanochemical copolymerization for highly selective separation of CO<sub>2</sub> from CO<sub>2</sub>/N<sub>2</sub>. *Chemical Engineering Journal*, 349, 92-100.
- Xian, S., Peng, J., Zhang, Z., Xia, Q., Wang, H., & Li, Z. (2015). Highly enhanced and weakened adsorption properties of two MOFs by water vapor for separation of CO<sub>2</sub>/CH<sub>4</sub> and CO<sub>2</sub>/N<sub>2</sub> binary mixtures. *Chemical Engineering Journal*, 270, 385-392.
- Xian, S., Xu, F., Ma, C., Wu, Y., Xia, Q., Wang, H., & Li, Z. (2015). Vapor-enhanced CO<sub>2</sub> adsorption mechanism of composite PEI@ ZIF-8 modified by polyethyleneimine for CO<sub>2</sub>/N<sub>2</sub> separation. *Chemical Engineering Journal*, 280, 363-369.
- Xu, F., Yu, Y., Yan, J., Xia, Q., Wang, H., Li, J., & Li, Z. (2016). Ultrafast room temperature synthesis of GrO@ HKUST-1 composites with high CO<sub>2</sub> adsorption capacity and CO<sub>2</sub>/N<sub>2</sub> adsorption selectivity. *Chemical engineering journal*, 303, 231-237.
- Zagho, M. M., Hassan, M. K., Khraisheh, M., Al-Maadeed, M. A. A., & Nazarenko, S. (2021). A review on recent advances in CO<sub>2</sub> separation using zeolite and zeolite-like materials as adsorbents and fillers in mixed matrix membranes (MMMs). *Chemical Engineering Journal Advances*, 6, 100091.
- Zhang, B., Liu, P., Huang, Z., & Liu, J. (2023). Adsorption equilibrium and diffusion of CH<sub>4</sub>, CO<sub>2</sub>, and N<sub>2</sub> in coal-based activated carbon. *ACS omega*, 8(11), 10303-10313.